



Den Braven

Montagefix High Grip

Versatile dispersion based adhesive with high initial tack



PRODUCT DESCRIPTION

Zwaluw Montagefix High Grip is a versatile adhesive based on acrylic dispersion with high initial tack. The adhesive cures due to evaporation of water to form a strong and durable bond.

KEY BENEFITS

- High initial tack and end strength (usually no support required during curing)
- Solvent free
- Suitable for EPS and XPS
- Paintable with water based and synthetic paints
- Perfect adhesion without use of primer on most, even slightly damp substrates
- Almost odourless
- Easy to apply and clean
- Non corrosive towards metals

APPLICATIONS

Zwaluw Montagefix High Grip was specifically developed for bonding wood, chipboard, hardboard and uPVC to brick work, stone or concrete. Also suitable for bonding EPS and XPS ornaments and decorative trims. For interior use.

DIRECTION FOR USE

Adhesion tests prior to the application are recommended. For the best results at least one of the two surfaces must be porous.

Panel applications:

- Apply Zwaluw Montagefix High Grip in 6 mm beads 5 cm from the edge and approximately 20 to 40 cm apart.
- Immediately press the panel firmly to the wall. Some support may be necessary for up to 24 hours.

Battens, skirting and other applications :

- Apply the adhesive equally in dots or stripes of 20 cm apart.

- The material must be put into place by moving slightly and applying an even pressure.
- Finally press firmly.
- Some support may be necessary for up to 24 hours.

TECHNICAL SPECIFICATIONS

Application Temperature		+5°C to +40°C
Base		Acrylic dispersion
Application Rate	@ Ø3 mm/4 bar	1000 g/min
Curing Time	@ +23°C/50% RH	1 day
Density	ISO 1183-1	1,30 g/ml
Flow	ISO 7390	< 2 mm
Frost Resistance		Up to - 15°C
Open Time	@ +23°C/50% RH	5-10 minutes
Temperature Resistance		-20°C to +75°C
Usage		400-600g/m ²

These are typical values

LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates, Not suitable for continuous exposure to water

SURFACE PREPARATIONS AND FINISHING

Application temperature +5°C to +40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Substrates to be cleared of all loose particles, absorbent substrates are not required to be fully dry. Very porous substrates like: gypsum, aerated concrete, limestone, etc, need to be primed with a mixture of 1 part Zwaluw Montagefix High Grip and 2 parts water. Always test adhesion prior to application.

PAINTABILITY

Zwaluw Montagefix High Grip is paintable after fully dry. During curing product will show shrinkage, which can cause cracking of the paint. Paintable with water based and synthetic paints. Painting with highly water based paints can create cracking. We recommend testing compatibility with paint prior to application.

CLEANING

Tools should be cleaned after use with water. Hands can be cleaned with Zwaluw Wipes and/or water and soap.

PACKAGING DESCRIPTION

- Cartridge

SHELF LIFE

In unopened original packaging between +5°C and +25°C, shelf life is up to 18 months from production date, stored in a dry place.

CERTIFICATIONS

- A+ French VOC Regulation
- Emission EC1 Plus



HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

WARRANTY & GUARANTEE

Bostik warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

