Den Braven

PU Thermo Adhesive B2

Professional B2 adhesive foam for external insulation facade systems

PRODUCT DESCRIPTION

Zwaluw PU Thermo Adhesive B2 is a moisture-curing one component low-expansion polyurethane adhesive for bonding and installation of Façade insulation boards (EWI/EIFS). Zwaluw PU Thermo Adhesive B2 cannot disolve after curing. It is waterproof, rot proof, permanently elastic and can be plastered. Zwaluw PU Thermo Adhesive B2 has a very good structure and excellent adhesion from + 5°C. Zwaluw PU Thermo Adhesive B2 is part of the product portfolio Sustainable Airtight Building Solutions. These products are tested to thermal insulation, driving rain and air loss. Correctly applied these products can contribute to energy savings of a building and therefore can come into close proximity with concepts such as passive house and energy neutral houses.

KEY BENEFITS

B2
Efficient bonding of facade insulation panels
Reduces labour time
No water and mixing on building site
No need for electricity
Reduces storage space on building site
Environmentally friendlier in comparison to traditional cement mortars

APPLICATIONS

Zwaluw PU Thermo Adhesive B2 can be used for highly efficient bonding and assembly of polystyrene (EPS, EPS-P, XPS etc.) rigid polyurethane foam (PUR/PIR) and mineral fiber panels to concrete, plaster and masonry, as well as for filling joints between the insulation boards.

DIRECTION FOR USE

Canister temperature: +5°C to +30°C (recommended +15°C to +25°C)
- Application temperature (applies to environment and substrates): -15°C to +35°C (recommended +15°C to +25°C)
- Hold the canister with the valve turned upwards and affix an applicator gun with NBS-thread to the canister. We recommend a NBS Gold (see instructions in the gun box). Shake the canister vigorously prior to use at least 20 times. Turn canister upside down and apply the foam. To regulate the flow of the foam, loosen the valve at the back of the handle. Fill the cavity for 70%, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. When fixing window frames, use spacers and wedges to hold the frame in place for approximately 24 hours until the foam is fully cured. Protect eyes, wear gloves and protective gear. Floor-covering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4 cm should be filled in multiple layers. Wait 15-30 minutes between applications. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding + 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking. For more information see Technical Bulletins in the Knowledge Base on our website www.denbraven.com.

TECHNICAL SPECIFICATIONS

Application Temperature		+5°C to +35°C
Base		Polyurethane
Curing Time		80-100 minutes
Density		15-20 kg/m3
Temperature Resistance		-40°C to +90°C
Cutting Time	FEICA TM1005	40-60 minutes
Fire Behaviour		B2
Joint sound insulation		61 dB
Tack free time	FEICA TM1014	8-12 minutes
Thermal conductivity		30-35 mW/m.K
Total foam yield		750 ml = 10-13 m²
Closed Cells		± 70%

These are typical values

LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates,Not suitable for permanent water load. Not suitable for use (eg filling) in cavities with insufficient moisture

SURFACE PREPARATIONS AND FINISHING

Surfaces must be clean, free of oil and grease. Moisten surfaces slightly using a spray bottle. When applying in cold conditions allow the canister to reach room temperature before use. Screw the can onto a pistol with NBS thread. Shake the can vigorously before use (at least 30 times). Protect eyes, wear gloves and protective gear. Tapestry, floor-covering and furniture to be covered with paper or plastic foil. Fresh product can be removed directly with Universal PU-Cleaner. After curing surplus foam can be removed with a knife or spatula and the surface can be finished.Bond the insulation panels by lining the plate in a continuous line with Den Braven® QF109GG 2 - 4cm from the edge. Leave no spaces. Apply at least one vertical bonding line in the middle of the plate. Attach within 2 minutes after application of foam, and bring into desired position. Any irregularity can be corrected within max. 20 minutes of bonding, depending on ambient temperature (air and substrate). Precise application is shown on the data sheet.

PAINTABILITY

Can be painted or covered with sealant/plaster when fully cured.

CLEANING

Fresh foam can be removed immediately with Zwaluw Universal PU-Cleaner. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

PACKAGING DESCRIPTION

- Aerosol
For product specifications, please refer to the Product Detail Page

SHELF LIFE

If kept stored in a cool, dry place, in unopened original packaging, between +5°C and +25°C, shelf life is up to 18 months from production date. Store the canisters in an upright position.

CERTIFICATIONS

- Emicode EC1 Plus – very low emission
- A+ French VOC Regulation

HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

WARRANTY & GUARANTEE

Bostik warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

ZWALUW®
HOTLINE
Smart help +31 162 491 000

Bostik S.A.
51, ESPLANADE DU GÉNÉRAL DE GAULLE
92800 PUTEAUX - LA DÉFENSE
TÉL. : +33 (1) 49 00 90 00