



Den Braven

Underbody Coating

Over-paintable



PRODUCT DESCRIPTION

Zwaluw Underbody Coating offers lasting and flexible protection from stone chipping and corrosion and is based on a combination of rubber and resin with roar-preventing effect.

APPLICATIONS

Especially suitable for motor vehicle bodies, wheel casings, front spoilers, car doors, edges, joints, bonnets, rear ends, deck lids, etc.

DIRECTION FOR USE

Ideal temperature +16°C to +25°C. Shake the aerosol for at least 2 minutes after the clearly audible striking of the metal ball. The parts to be treated must be clean, dry and free of grease, oil and rust. Apply the underseal in as even a layer as possible. Spray from a distance of 25–30 cm. Don't spray it on engine, brake and exhaust parts or on moveable parts. Turn the aerosol up after use and empty the valve.

TECHNICAL SPECIFICATIONS

Application Temperature	+16°C to +25°C
Base	Rubber resin
Curing Time	24 hours
Density	0.900
Frost Resistance	Up to -15°C
Tack free time	50-60 minutes
Pressure at 20°C [bar]	4.8
Pressure at 50°C [bar]	8.1
Extrusion rate [g/s]	2.3
Temperature range [°C]	-20°C to +70°C
Dust free after [min]	120 minutes

These are typical values

SURFACE PREPARATIONS AND FINISHING

The parts to be treated must be clean, dry and free of grease, oil and rust.

SHELF LIFE

Storage between +5°C and +25°C and in shaded conditions. Shelf life is 24 months when stored as recommended in original unopened packaging.

HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

WARRANTY & GUARANTEE

Bostik warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what

way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



HOTLINE

Smart help +31 162 491 000